## LG Water Solutions



# **Data Sheet**



Brackish Water Reverse Osmosis (RO) Membranes

#### **LG BW 440 R G2**

Superior Rejection, High Flow, High Durability

#### **Overview**


LG Chem's NanoH<sub>2</sub>O<sup>™</sup> brackish water RO membranes serve various municipal and industrial applications and have been operating in the major utilities around the world. Incorporating innovative Thin Film Nanocomposite (TFN) technology, all LG BWRO membranes provide superior performance along with intrinsic anti-fouling property and are suitable for applications where consistent and reliable performance is a must.

LG BW 440 R G2 membranes offer a combination of superior rejection, flow and durability and reduce total cost of ownership: suitable for high salinity brackish water and wastewater reuse applications.

### **Product Specifications**

Active Membrane	Permeate flow rate, GPD (m³/d)	Stabilized Salt	Minimum Salt	Feed Spacer,
Area, ft <sup>2</sup> (m <sup>2</sup> )		Rejection, %	Rejection, %	mil
440 (41)	12,650 (47.9)	99.78	99.65	28

Test Conditions: 2,000 ppm NaCl at 25°C (77°F), 225 psi (15.5 bar), pH 7, Recovery 15%. Permeate flows for individual elements may vary +/-15%.



A,	B,	C,	Weight,
mm (in.)	mm (in.)	mm (in.)	kg (lbs.)
1,016	200	28.6	16
(40)	(7.9)	(1.125)	(35)

All dimensional information is indicative and for reference purpose only. Please contact LG Chem for detailed technical specification.

# **Operating Specifications**

For more information and operating guidelines, visit  $\underline{www.lgwatersolutions.com}$ 

Max. Applied pressure	600 psi (41 bar)
Max. Chlorine concentration	< 0.1 ppm
Max. Operating temperature	45°C (113°F)
pH Range, Continuous (Cleaning)	2-11 (1-13)
Max. Feedwater turbidity	1.0 NTU
Max. Feedwater SDI (15 mins)	5.0
Max. Feed flow	75 gpm (17 m <sup>3</sup> /h)
Max. Pressure drop (ΔP) for each element	15 psi (1.0 bar)

The information and data contained herein are deemed to be accurate and reliable and are offered in good faith, but without guarantee of performance. LG Chem assumes no liability for results obtained or damages incurred through the application of the information contained herein. Customer is responsible for determining whether the products and information presented herein are appropriate for the customer's use and for ensuring that customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Specifications subject to change without notice. NanoH<sub>2</sub>O is the Trademark of The LG Water Solutions or an affiliated company of LG Chem. All rights reserved. © LG Chem, Ltd.

Rev. A (03.15)

